

STANDARD FLY ASH CERTIFICATE



FINAL
Prior Reports: None

Flyash Australia Pty Ltd
ABN 68 002 840 271
P.O. Box 190
Eastwood NSW 2122
Email: contact@flyash.com.au
www.flyashaustralia.com.au

Certificate Number: CERT240277
Issued: 05 February 2024

Product being certified: Eraring Monthly Grab Fly Ash
Product sample date: 04-Jan-2024
Sample Identification: Sample Code: 24010896
Source Power Station: Eraring Power Station
Sample Condition: Tested as Received. Testing Commenced on 10-Jan-2024
Certifying Laboratory: Cement Australia - Darra Laboratory,
18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

| Test | Moisture % | Fineness @ 45 micron % Passed | Loss on Ignition % | Sulfuric Anhydride % | Available Alkali % | Chloride Ion % | Chemical Composition % |
|-------------|---------------|-------------------------------------|--------------------------|----------------------------|--------------------------|----------------------|------------------------------|
| Result | < 0.1 | 88 | 1.7 | 0.1 | Not Tested | < 0.002 | 93 |
| Test Method | AS3583.2 | AS3583.1 | AS3583.3 | AS2350.2 | AS3583.12 | AS3583.13 | AS2350.2 |
| AS 3582.1 | 0.5 % Maximum | 75% Minimum | 4.0 % Maximum | 3.0 % Maximum | - | 0.1 % Maximum | 70% Minimum |

| Test | Relative Density | Relative Water Requirement % | Strength Index 7 Day Acc. % | Reference Cement Details |
|-------------|---------------------|------------------------------------|-----------------------------------|---|
| Result | 2.15 | 97 | 92 | Identification:: 24010964 Source: Goliath GP |
| Test Method | AS3583.5 | AS3583.6 | AS3583.6 | Product Type: Type GP |
| AS 3582.1 | - | - | 75% Minimum | Sample Date: 12-Jan-24 |

Additional Testing - Oxides


| Test | CaO by XRF % | SiO ₂ by XRF % | Al ₂ O ₃ by XRF % | Fe ₂ O ₃ by XRF % | SO ₃ by XRF % | MgO by XRF % | Na ₂ O by XRF % |
|-------------|--------------------|---------------------------------|---|---|--------------------------------|--------------------|----------------------------------|
| Result | 1.8 | 68.0 | 19.9 | 4.6 | 0.1 | 0.8 | 0.45 |
| Test Method | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 |

| Test | K ₂ O by XRF % | SrO by XRF % | TiO ₂ by XRF % | P ₂ O ₅ by XRF % | Mn ₂ O ₃ by XRF % | Total Alkali (NaEQ) % |
|-------------|---------------------------------|--------------------|---------------------------------|--|---|-----------------------------|
| Result | 1.35 | <0.1 | 0.9 | 0.4 | < 0.1 | 1.34 |
| Test Method | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 | AS2350.2 |

This sample grade conforms to the following requirements of AS 3582.1:2016


| Special | Grade 1 | Grade 2 |
|---------|---------|---------|
| | X | |

Approved Signatory



A Prem
Signatory - Cement Australia
Chemical Testing
Construction Materials Testing

Accredited for compliance with ISO/IEC 17025 - Testing
NATA is a signatory to the ILAC Mutual Recognition
Arrangement for the mutual recognition of the
equivalence of testing, medical testing, calibration,
inspection, proficiency testing scheme providers and
reference materials producers reports and certificates.



Laboratory accreditation number: 188
Laboratory accreditation number: 187

WORLD RECOGNISED
ACCREDITATION

Notes:

